

U.S. Patent Application Serial No. 10/531,952

Amendment filed November 5, 2008

Reply to OA dated October 10, 2008

AMENDMENTS TO THE ABSTRACT:

Please amend the abstract as follows:

Disclosed is a resin composition that has excellent impact resistance and excellent heat resistance without substantially deteriorating biodegradability that the lactic acid based resin has inherently. The resin composition includes component (A), which is a lactic acid based resin; and component (B), which is an aromatic aliphatic polyester having a glass transition temperature (T_g) of 0°C or less and a heat of crystal melting (ΔH_m) of 5 J/g to 30 J/g, and/or an aliphatic polyester other than the lactic acid based resin, having a glass transition temperature (T_g) of 0°C or less and a heat of crystal melting (ΔH_m) of 5 J/g to 30 J/g ~~[[,]] . and Component (B) an aromatic aliphatic polyester having a glass transition temperature (T_g) of 0°C or less and a heat of crystal melting (ΔH_m) of 5 J/g to 30 J/g, and/or an aliphatic polyester other than the lactic acid based resin, having a glass transition temperature (T_g) of 0°C or less and a heat of crystal melting (ΔH_m) of 5 J/g to 30 J/g,~~ has a content of 5 mass% to 25 mass% in the resin composition.